



Barit Maden Türk A.Ş.



Intertek

BMT ZENGİNLEŞTİRİLMİŞ SELESTİT TEKNİK ÖZELLİKLERİ
BMT CONCENTRATED CELESTITE TECHNICAL DATA SHEET

KİMYASAL ANALİZLER CHEMICAL ANALYSIS	BİRİM UOM	KONSANTRE SELESTİT CONCENTRATED CELESTITE
SrSO ₄	%	85-94
BaSO ₄	%	< 2
CaSO ₄	%	< 1.5
CaCO ₃	%	< 2
SiO ₂	%	< 1
Fe ₂ O ₃	%	< 0.5
MgO	%	< 0.1
Al ₂ O ₃	%	< 0.1

FİZİKSEL ÖZELLİKLER PHYSICAL PROPERTIES	BİRİM UOM	KONSANTRE SELESTİT CONCENTRATED CELESTITE
Yoğunluk Density	g/cm ³	3,75 (min)
Sertlik Hardness	Moh's	3-3,5

TANE BOYUTU DAĞILIMI (Malvern Mastersizer MU 2000E) PARTICLE SIZE DISTRIBUTION (Malvern Mastersizer MU 2000E)	BİRİM UOM	KONSANTRE SELESTİT CONCENTRATED CELESTITE
Tane Boyutu (D90) Particle Size (D90)	mm	15 (max)

PAKETLEME | PACKAGING

1000 kg Big Bag Torba ve Dökme Taşıma
1000 kg Big Bag and Bulk Shipment

BARIT MADEN TURK A.S.

Cumhuriyet Cad.Pak Apt.No:30 Kat:6 D:13 Şişli - İstanbul / TÜRKİYE

e-mail: info@baritmaden.com

Tel: + 90 212 234 12 06

Fax: + 90 212 234 12 14

www.baritmaden.com